



PCT/482004/004973



INVESTOR IN PEOPLE


The Patent Office  
Concept House  
Cardiff Road  
Newport  
South Wales  
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.



Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed

*Stephen Hordley*

Dated 15 December 2004



# Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

26 JUN 2004

The Patent Office

Cardiff Road  
 Newport  
 Gwent NP9 1RH

1. Your reference	SMC 60662/GB/P1		
2. Patent application number (The Patent Office will fill in this part)	0414347.5		
3. Full name, address and postcode of the or of each applicant (underline all surnames)	Avecia Limited Hexagon House Blackley Manchester, M9 8ZS		
Patents ADP number (if you know it)  If the applicant is a corporate body, give the country/state of its incorporation	07764137001 ✓  United Kingdom		
4. Title of the invention	Improvements in and relating to organic semiconducting layers		
5. Name of your agent (if you have one)	REVELL, Christopher		
"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)	Avecia Limited Hexagon House PO Box 42 Blackley Manchester M9 8ZS		
Patents ADP number (if you know it)	<del>0969885001</del> 07764137001		
6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number	Country	Priority application number (if you know it)	Date of filing (day / month / year)
7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application	Number of earlier application	Date of filing (day / month / year)	
8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:			
a) any applicant named in part 3 is not an inventor, or b) there is an inventor who is not named as an applicant, or c) any named applicant is a corporate body. See note (d))	Yes		

**Patents Form 1/77**

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description

42

Claim(s)

Abstract

Drawing(s)

1 & 1

ly

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77)

Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

11.

I/We request the grant of a patent on the basis of this application.

Signature

G. Shepherd

Date

25/6/2004

Avecia Limited Authorised Signatory

12. Name and daytime telephone number of person to contact in the United Kingdom

K.M.Pinder/G.Shepherd 0161 721 1361/2

**Warning**

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

**Notes**

- a) If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- b) Write your answers in capital letters using black ink or you may type them.
- c) If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- d) If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- e) Once you have filled in the form you must remember to sign and date it.
- f) For details of the fee and ways to pay please contact the Patent Office.

## IMPROVEMENTS IN AND RELATING TO ORGANIC SEMICONDUCTING LAYERS

The present invention relates to an organic semiconducting layer formulation, a layer comprising the same, a process for preparing the formulation and layer and electronic devices (including OFETs) comprising the same.

In recent years, there has been development of organic semiconducting materials in order to produce more versatile, lower cost electronic devices. Such materials find application in a wide range of devices or apparatus, including organic field effect transistors (OFETs), organic light emitting diodes (OLEDs), photodetectors, photovoltaic (PV) cells, sensors, memory elements, logic circuits and as organic photoconductors (OPCs) in electrophotographic devices, to name just a few. The organic semiconducting materials are typically present in the electronic device in the form of a thin layer, for example less than 1 micron thick.

Pentacene has shown promise as an organic semiconducting material. Pentacene though has been described as requiring a highly crystalline structure in order to provide a molecular orientation which results in good charge mobility. Thus, pentacene thin films have been vapour deposited in the prior art (pentacene is also rather insoluble in common solvents). However, vapour deposition requires expensive and sophisticated equipment. In view of the latter problem, another approach has been to apply a solution containing a precursor pentacene and then chemically converting, for example by heat, the precursor compound into pentacene. However, the latter method is also complex and it is difficult to control in order to obtain the necessary ordered structure for good charge mobility.

Soluble pentacene compounds have recently been described in the prior art as organic semiconducting compounds, see for example US 2003/0116755 A (Takahashi) and US 6,690,029 (Anthony) and their use in FETs has been suggested in WO 03/016599 (Asahi). In the latter reference, a solution of the soluble pentacene was deposited on a substrate and the solvent evaporated to form a thin film of the pentacene. However, the soluble pentacenes have been described in US 6,690,029 and WO 03/016599 as still requiring a highly crystalline structure in the thin film for acceptable charge mobility, especially when used in FETs, which means that the pentacenes must still be carefully deposited. Thus, the prior art is careful not to dilute the pentacene in any way, otherwise it would be expected to disrupt the crystalline structure of the pentacene and hence reduce charge mobility.


Improved charge mobility is one goal of new electronic devices. Another goal is the stability and integrity of the organic semiconductor layer. A way potentially to improve organic semiconductor layer stability and integrity in devices would be to include the organic semiconducting component in an organic binder resin. However, whenever an organic semiconducting component is combined with a binder it is effectively "diluted" by the binder and a reduction of charge mobility is to be expected. Among other things,

diluting an organic semiconductor by mixing with binders disrupts the molecular order in the semiconducting layer. Diluting an organic semiconducting component in the channel of an OFET for example is particularly problematic as any disruption of the orbital overlap between molecules in the immediate vicinity of the gate insulator (the first few molecular layers) is expected to reduce mobility. Electrons or holes are then forced to extend their path into the bulk of the organic semiconductor, which is undesirable. Certain organic semiconducting materials are expected to be more susceptible than others to the effects of use in a binder. Since pentacenes have been taught as requiring highly ordered structures for useful charge mobility, it has not previously been considered desirable to include pentacenes with binders. In WO 03/030278 (Philips) it was attempted to use binders but there it was shown that a gradual reduction of FET mobility occurs when a (precursor) pentacene is mixed with increasing amounts of binder, even with amounts of less than 5% binder.

Certain low polarity binder resins are described in WO 02/45184 (Avecia) for use with organic semiconductors in FETs. However, a reduction in charge mobility is still expected when the semiconductor is diluted in the binder.

Among the objects of the present invention is the aim to reduce or overcome the disadvantages in organic semiconducting layers described above.

According to the present invention there is provided an organic semiconducting layer formulation, which layer formulation comprises an organic binder resin and a polyacene compound of Formula A:



Formula A

wherein each of  $R_1$ ,  $R_2$ ,  $R_3$ ,  $R_4$ ,  $R_5$ ,  $R_6$ ,  $R_7$ ,  $R_8$ ,  $R_9$ ,  $R_{10}$ ,  $R_{11}$  and  $R_{12}$ , which may be the same or different, independently represents hydrogen; an optionally substituted  $C_1$ - $C_{40}$  carbyl or hydrocarbyl group; an optionally substituted  $C_1$ - $C_{40}$  alkoxy group; an optionally substituted  $C_6$ - $C_{40}$  aryloxy group; an optionally substituted  $C_7$ - $C_{40}$  alkylaryloxy group; an optionally substituted  $C_2$ - $C_{40}$  alkoxy carbonyl group; an optionally substituted  $C_7$ - $C_{40}$  aryloxy carbonyl group; a cyano group ( $-CN$ ); a carbamoyl group ( $-C(=O)NH_2$ ); a haloformyl group ( $-C(=O)-X$ , wherein  $X$  represents a halogen atom); a formyl group ( $-C(=O)-H$ ); an isocyano group; an isocyanate group; a thiocyanate group or a thioisocyanate group; an optionally substituted amino group; a hydroxy group; a nitro group; a  $CF_3$  group; a halo group; or an optionally substituted silyl group; and

wherein each pair of  $R_2$  and  $R_3$  and/or  $R_8$  and  $R_9$  may be cross-bridged to form a

C<sub>4</sub>-C<sub>40</sub> saturated or unsaturated ring, which saturated or unsaturated ring may be intervened by an oxygen atom, a sulphur atom or a group shown by formula -N(R<sub>a</sub>)- (wherein R<sub>a</sub> is a hydrogen atom or an optionally substituted hydrocarbon group), or may optionally be substituted; and


wherein one or more of the carbon atoms of the polyacene skeleton may optionally be substituted by a heteroatom selected from N, P, As, O, S, Se and Te; and

wherein any two or more of the substituents R<sub>1</sub>-R<sub>12</sub> which are located on adjacent ring positions of the polyacene may, together, optionally constitute a further C<sub>4</sub>-C<sub>40</sub> saturated or unsaturated ring optionally interrupted by O, S or -N(R<sub>a</sub>) where R<sub>a</sub> is as defined above) or an aromatic ring system, fused to the polyacene; and wherein

n is 0, 1, 2, 3 or 4 preferably n is 0, 1 or 2, most preferably n is 0 or 2 that is the polyacene compound is a pentacene compound or 'pseudo pentacene' compound.


More preferably, the pentacene compound is a compound selected from any one of Compound Groups 1 to 9 or isomers thereof wherein:

Compound Group 1 is represented by Formula 1:




Formula 1

Compound Group 2 is represented by Formula 2:




Formula 2

Compound Group 3 is represented by Formula 3:




Formula 3

Compound Group 4 is represented by Formula 4:




Formula 4

Compound Group 5 is represented by Formula 5:




Formula 5

Compound Group 6 is represented by Formula 6:



Formula 6


Compound Group 7 is represented by Formula 7:



Formula 7

Compound Group 8 is represented by Formula 8:


5



Formula 8

Compound Group 9 is represented by the Formula 9:

5




Formula 9

10 and wherein, in the case of Compound Group 1  $R_6$  and  $R_{13}$ , in the case of Compound Group 2  $R_5$  and  $R_{14}$ , in the case of Compound Group 3  $R_2$ ,  $R_3$ ,  $R_9$  and  $R_{10}$ , in the case of Compound Group 4  $R_2$  and  $R_3$ , in the case of Compound Group 5  $R_2$ ,  $R_3$ ,  $R_{11}$  and  $R_{12}$ , in the case of Compound Group 6  $R_2$  and  $R_9$ , in the case of Compound Group 7  $R_6$ ,  $R_7$ ,  $R_{12}$  and  $R_{14}$ , in case of Group 8  $R_1$ ,  $R_2$ ,  $R_3$ ,  $R_4$ ,  $R_8$ ,  $R_9$ ,  $R_{10}$ ,  $R_{11}$ ,  $R_{15}$ ,  $R_{16}$ ,  $R_{17}$  and  $R_{18}$ , and in  
 15 the case of Group 9  $R_2$ ,  $R_3$ ,  $R_7$ ,  $R_8$ ,  $R_{15}$ ,  $R_{16}$ ,  $R_{17}$ , each independently represents an optionally substituted  $C_1$ - $C_{40}$  carbyl or hydrocarbyl group; an optionally substituted  $C_1$ - $C_{40}$  alkoxy group; an optionally substituted  $C_6$ - $C_{40}$  aryloxy group; an optionally substituted  $C_7$ - $C_{40}$  alkylaryloxy group; an optionally substituted  $C_2$ - $C_{40}$  alkoxy carbonyl group; an optionally substituted  $C_7$ - $C_{40}$  aryloxy carbonyl group; a cyano group ( $-CN$ ); a carbamoyl group ( $-C(=O)NH_2$ ); a haloformyl group ( $-C(=O)-X$ , wherein  $X$  represents a halogen atom);  
 20 a formyl group ( $-C(=O)-H$ ); an isocyano group; an isocyanate group; a thiocyanate group or a thioisocyanate group; an optionally substituted amino group; a hydroxy group; a nitro group; a  $CF_3$  group; a halo group; or an optionally substituted silyl group; and wherein



independently each pair of  $R_1$  and  $R_2$ ,  $R_2$  and  $R_3$ ,  $R_3$  and  $R_4$ ,  $R_9$  and  $R_{10}$ ,  $R_{10}$  and  $R_{11}$ , and  $R_{15}$ ,  $R_{16}$  and  $R_{16}$ ,  $R_{17}$  may be cross-bridged with each other to form a  $C_4$ - $C_{40}$  saturated or unsaturated ring, which saturated or unsaturated ring may be intervened by an oxygen atom, a sulphur atom or a group shown by formula:  $-N(R_a)-$  (wherein  $R_a$  is a hydrogen atom or a hydrocarbon group), or may optionally be substituted.

The "R" substituents (that is,  $R_1$ ,  $R_2$ , etc.) in Compound Groups 1-9 denote the substituents at the positions of pentacene according to conventional nomenclature:



Surprisingly and beneficially, the inventors of the present invention have found that combining the specified soluble polyacene compounds, especially the pentacene compounds from Compound Groups 1-9, (hereinafter often referred to as "the polyacene") with an organic binder resin (hereinafter sometimes simply called a "binder") results in little or no reduction in charge mobility of the polyacene, even an increase in some instances. For instance, the soluble polyacene may be dissolved in a binder resin (for example polystyrene) and deposited (for example by spin coating), to form an organic semiconducting layer yielding a high charge mobility, for example  $0.3 \text{ cm}^2/\text{Vs}$ . This result is particularly unexpected given that the prior art teaches that for such high mobilities a polyacene derivative compound is expected to require strong molecular ordering. Dilution in a binder would be expected to yield an order of magnitude reduction in mobility. We have found that surprisingly even at a 1:1 ratio of binder:polyacene the mobility is about the same as that of the pure polyacene compound. The results produced by the present invention are therefore surprising for both a) maintaining the mobility despite potential disruption of molecular order, and b) maintaining mobility despite the expected increase of intermolecular distance. It is particularly surprising that the size of crystalline grains is reduced upon using a binder yet the mobility is high. At the same time, a semiconducting layer formed therefrom exhibits excellent film forming characteristics and is particularly stable.

Once a formulation of high mobility is obtained by combining the polyacene with the binder, the resulting formulation leads to several other advantages. Since the polyacenes are soluble they may be deposited in a liquid form, for example from solution. With the additional use of the binder we have found that the formulation may be coated on a large area in a highly uniform manner. Without the use of binders the polyacene cannot be spin coated on large areas as it does not result in uniform films. In the prior art, spin and drop-casting of a pure polyacene layer may in some cases result in relatively high mobility but it is difficult to provide a film with a constant mobility over the entire substrate.

Second, it is possible to control the properties of the formulation to adjust to printing processes, for example viscosity, solid content, surface tension. It is also anticipated that the binder fills in volume between crystalline grains otherwise being void, making the organic semiconducting layer less sensitive to air and moisture. For example, layers formed according to the present invention show very good stability in OFET devices in air.

The invention also provides an organic semiconducting layer which comprises the organic semiconducting layer formulation.


The invention further provides a process for preparing the organic semiconducting layer which comprises (i) depositing on a substrate a liquid layer of a mixture which comprises the polyacene compound, the organic binder resin or precursor thereof and optionally a solvent, and (ii) forming from the liquid layer a solid layer which is the organic semiconducting layer. The process is described in more detail below.

The invention additionally provides an electronic device comprising the said organic semiconducting layer. The electronic device may include, without limitation, an organic field effect transistor (OFET), organic light emitting diode (OLED), photodetector, sensor, logic circuit, memory element, capacitor or photovoltaic (PV) cell. For example, the active semiconductor channel between the drain and source in an OFET may comprise the layer of the invention. As another example, a charge (hole or electron) injection or transport layer in an OLED device may comprise the layer of the invention. The organic semiconducting layer may also find use forming at least part of an organic photoconductor (OPC) in an electrophotographic device. The formulation of the present invention and layers formed therefrom have particular utility in OFETs. Certain polyacene compounds have been described in US 2003/0116755 A and US 6,690,029 and the methods disclosed therein for synthesising the polyacenes may be employed in the present invention in order to make the polyacene compounds. Methods for making the polyacenes are also described in US 3,557,233 (American Cyanamid). Alternative methods within the skill and knowledge of persons skilled in the art which may be used to synthesise polyacene compounds are disclosed in Organic Letters 2004, Volume 6, number 10, pages 1609-1612.

Compound Groups 1-9 are now described in more detail.

#### Compound Group 1


Compound Group 1 is represented by Formula 1:




Formula 1

In pentacene derivatives of Compound Group 1,  $R_6$  and  $R_{13}$  are preferably the same substituent as each other. Preferably, the groups  $R_6$  and  $R_{13}$  comprise optionally substituted  $C_1$ - $C_{40}$  carbyl or hydrocarbyl groups. More preferably, the groups  $R_6$  and  $R_{13}$  comprise optionally substituted unsaturated  $C_1$ - $C_{40}$  carbyl or hydrocarbyl groups, for example optionally substituted alkenyl, alkynyl, aryl etc. groups (optionally substituted alkynyl is a preferred group, especially optionally substituted ethynyl). Preferably, the  $R_6$  and  $R_{13}$  substituents are  $\pi$ -conjugated with the pentacene ring structure. In pentacene derivatives of Compound Group 1 none of the ring positions on the pentacene other than the 6 and 13 positions are substituted, that is they are occupied by hydrogen.

Examples of Compound Group 1 are given below:




Group 1, example 1



Group 1, example 2

15 Compound Group 2

Compound Group 2 is represented by Formula 2:




Formula 2

In pentacene derivatives of Compound Group 2,  $R_5$  and  $R_{14}$  are preferably the same substituent as each other. Preferably, the groups  $R_5$  and  $R_{14}$  comprise optionally substituted  $C_1$ - $C_{40}$  carbyl or hydrocarbyl groups. More preferably, the groups  $R_5$  and  $R_{14}$  comprise optionally substituted unsaturated  $C_1$ - $C_{40}$  carbyl or hydrocarbyl groups, for example optionally substituted alkenyl, alkynyl, aryl, aralkyl groups (optionally substituted alkynyl is a preferred group, especially optionally substituted ethynyl). Preferably, the  $R_5$  and  $R_{14}$  substituents are  $\pi$ -conjugated with the pentacene ring structure. In pentacene derivatives of Compound Group 2 one or more of the ring positions on the pentacene derivatives other than the 5 and 14 positions may be substituted but preferably they are unsubstituted, that is they are occupied by hydrogen.

### Compound Group 3

Compound Group 3 is represented by Formula 3:




Formula 3

In pentacene derivatives of Compound Group 3,  $R_2$  and  $R_3$  are preferably the same substituent as each other, and  $R_9$  and  $R_{10}$  are preferably the same substituent as each other. Preferably,  $R_2$ ,  $R_3$ ,  $R_9$  and  $R_{10}$  are the same substituent as each other. Preferably, the groups  $R_2$ ,  $R_3$ ,  $R_9$  and  $R_{10}$  comprise optionally substituted  $C_1$ - $C_{40}$  carbyl or hydrocarbyl groups. Further preferably, the groups  $R_2$ ,  $R_3$ ,  $R_9$  and  $R_{10}$  comprise optionally substituted  $C_1$ - $C_{10}$  carbyl or hydrocarbyl groups (especially alkyl), for example methyl, ethyl, propyl, butyl, pentyl, etc. One or more of the ring positions on the pentacene other than the 2, 3, 9 and 10 positions may be substituted but preferably they are unsubstituted, that is they are occupied by hydrogen.

An example of Compound Group 3 is given below:


10



Group 3, example

Compound Group 4


Compound Group 4 is represented by Formula 4:



Formula 4

In pentacene derivatives of Compound Group 4, R<sub>2</sub> and R<sub>3</sub> are preferably the same substituent as each other. Preferably, the groups R<sub>2</sub> and R<sub>3</sub> comprise optionally substituted C<sub>1</sub>-C<sub>40</sub> carbyl or hydrocarbyl groups or halo. In pentacene derivatives of Compound Group 4, one or more of the ring positions on the pentacene other than the 2 and 3 positions may be substituted but preferably they are unsubstituted, that is they are occupied by hydrogen.


An example of Compound Group 4 is given below:



Group 4 example

Compound Group 5


Compound Group 5 is represented by Formula 5:



Formula 5

In pentacene derivatives of Compound Group 5, R<sub>2</sub> and R<sub>3</sub> are preferably the same substituent as each other, and R<sub>11</sub> and R<sub>12</sub> are preferably the same substituent as each other. Preferably, R<sub>2</sub>, R<sub>3</sub>, R<sub>11</sub> and R<sub>12</sub> are the same substituent as each other. Preferably, the groups R<sub>2</sub>, R<sub>3</sub>, R<sub>11</sub> and R<sub>12</sub> comprise optionally substituted C<sub>1</sub>-C<sub>40</sub> carbyl or hydrocarbyl groups. Further preferably, the groups R<sub>2</sub>, R<sub>3</sub>, R<sub>11</sub> and R<sub>12</sub> comprise


optionally substituted C<sub>1</sub>-C<sub>10</sub> carbyl or hydrocarbyl groups, for example methyl, ethyl, propyl, butyl, pentyl, etc. In pentacene derivatives of Compound Group 5, one or more of the ring positions on the pentacene derivative other than the 2, 3, 11 and 12 positions may be substituted but preferably, they are unsubstituted, that is they are occupied by hydrogen. An example of Compound Group 5 is given below:



Group 5, example

#### Compound Group 6


Compound Group 6 is represented by Formula 6:



Formula 6

In pentacene derivatives of Compound Group 6, R<sub>2</sub> and R<sub>9</sub> are preferably the same substituent as each other. Preferably, the groups R<sub>2</sub> and R<sub>9</sub> comprise optionally substituted C<sub>1</sub>-C<sub>40</sub> carbyl or hydrocarbyl groups. In pentacene derivatives of Compound Group 6, one or more of the ring positions on the pentacene other than the 2 and 9 positions may be substituted but preferably they are unsubstituted, that is they are occupied by hydrogen.

An example of a Compound of Group 6 is given below:




Group 6 example

#### Compound Group 7

Compound Group 7 is represented by Formula 7:


12



Formula 7

In pentacene derivatives of Compound Group 7,  $R_5$  and  $R_{14}$  are preferably the same substituent as each other.  $R_7$  and  $R_{12}$  are preferably the same substituent as each other. Preferably,  $R_5$ ,  $R_{14}$ ,  $R_7$  and  $R_{12}$  are all the same substituent as each other. Preferably, the groups  $R_5$ ,  $R_{14}$ ,  $R_7$  and  $R_{12}$  comprise optionally substituted  $C_1$ - $C_{40}$  carbyl or hydrocarbyl groups. In pentacene derivatives of Compound Group 7, one or more of the ring positions on the pentacene other than the 5, 14, 7 and 12 positions may be substituted but preferably they are unsubstituted, that is they are occupied by hydrogen.


An example of a Compound of Group 7 is given below:



Group 7 example

### Compound Group 8

Compound Group 8 is represented by Formula 8:



Formula 8

In pentacene derivatives of Compound Group 8 and isomers thereof,  $R_1$  and  $R_2$ ,  $R_2$   
 5 and  $R_3$ ,  $R_3$  and  $R_4$  are preferably the same substituent as each other and  $R_8$  and  $R_9$ ,  $R_9$   
 and  $R_{10}$  and  $R_{10}$  and  $R_{11}$  are preferably the same substituent as each other. Most  
 preferably  $R_1$ ,  $R_2$ ,  $R_3$ ,  $R_4$ ,  $R_8$ ,  $R_9$ ,  $R_{10}$  and  $R_{11}$  are the same substituent as each other.  
 Preferably groups  $R_1$ ,  $R_2$ ,  $R_3$ ,  $R_4$ ,  $R_8$ ,  $R_9$ ,  $R_{10}$  and  $R_{11}$  comprises optionally substituted  $C_{1-40}$   
 carbyl or hydrocarbyl groups. More preferably, the groups  $R_1$ ,  $R_2$ ,  $R_3$ ,  $R_4$ ,  $R_8$ ,  $R_9$ ,  $R_{10}$  and  
 10  $R_{11}$  comprise optionally substituted unsaturated  $C_{1-40}$  carbyl or hydrocarbyl groups, for  
 example optionally substituted alkenyl, alkynyl, aryl etc groups or halo groups for example  
 F, Cl, Br. More preferably,  $R_2$ ,  $R_3$ ,  $R_9$  and  $R_{10}$  comprise optionally substituted  $C_{1-10}$  carbyl  
 or hydrocarbyl groups for example methyl, ethyl, propyl, butyl, pentyl etc. or  $R_2$ , and  $R_3$ ,  $R_9$   
 and  $R_{10}$  together with the carbon atoms to which they are attached form a  $C_4-C_{40}$   
 15 saturated or unsaturated ring, more preferably an optionally substituted  $C_4-C_{10}$  saturated  
 or unsaturated ring, intervened by one or more oxygen or sulphur atoms or a group  
 represented by formula  $-N(R_a)$ , wherein  $R_a$  is a hydrogen atom or a hydrocarbon group,  
 and  $R_1$ ,  $R_4$ ,  $R_8$  and  $R_{11}$  comprise a halo group, preferably F. In the pentacene derivatives  
 of Formula 8,  $R_{15}$ ,  $R_{16}$  and  $R_{17}$  may be the same or different most preferably  $R_{15}$ ,  $R_{16}$  and  
 20  $R_{17}$  are the same and comprise hydrogen, a  $C_1-C_{40}$  alkyl group (preferably  $C_1-C_4$  alkyl and  
 most preferably methyl, ethyl, n-propyl or isopropyl) which may optionally be substituted  
 for example with a halogen atom; a  $C_6-C_{40}$  aryl group (preferably phenyl) which may  
 optionally be substituted for example with a halogen atom; a  $C_6-C_{40}$  arylalkyl group which  
 may optionally be substituted for example with a halogen atom; a  $C_1-C_{40}$  alkoxy group  
 25 which may optionally be substituted for example with a halogen atom; or a  $C_6-C_{40}$   
 arylalkoxy group which may optionally be substituted for example with a halogen atom or  
 $R_{15}$  and  $R_{16}$  or  $R_{16}$  and  $R_{17}$  together with the silicon atom to which they are attached form a  
 $C_4-C_{40}$  saturated or unsaturated ring, more preferably an optionally substituted  $C_4-C_{10}$   
 saturated or unsaturated ring, intervened by one or more oxygen or sulphur atoms or a  
 30 group represented by formula  $-N(R_a)$ , wherein  $R_a$  is a hydrogen atom or a hydrocarbon  
 group and/or isomers thereof. Preferably,  $R_{15}$ ,  $R_{16}$  and  $R_{17}$  are each independently




selected from optionally substituted  $C_{1-10}$  alkyl (more preferably  $C_{1-4}$  and even more preferably  $C_{1-3}$  alkyl, for example isopropyl) and optionally substituted  $C_{6-10}$  aryl (preferably phenyl).

In one preferred embodiment of silyl group,  $R_{15}$ ,  $R_{16}$  and  $R_{17}$  are preferably the same group as each other, for example the same optionally substituted alkyl group, as in triisopropylsilyl. Preferably, in that preferred embodiment, the groups  $R_{15}$ ,  $R_{16}$  and  $R_{17}$  are the same optionally substituted  $C_{1-10}$  (more preferably  $C_{1-4}$  and even more preferably  $C_{1-3}$ ) alkyl group. A preferred alkyl group in this case is isopropyl.


A silyl group of formula  $-\text{Si}(R_{15})(R_{16})(R_{17})$  as described above is a preferred optional substituent for the  $C_1$ - $C_{40}$  carbonyl or hydrocarbonyl group etc.

In the pentacene derivatives of compound Group 8 one or more of the ring positions on the pentacene derivative other than the 1, 2, 3, 4, 6, 8, 9, 10, 11 and 13 positions may be substituted, but preferably they are unsubstituted, that is, they are occupied by hydrogen.

Examples of Compound Group 8 compounds are given below:




Group 8, example 1




Group 8, example 2

15



Group 8, example 3




Group 8, example 4

5

### Compound Group 9

Compound Group 9 is represented by Formula 9:


0




Formula 9

15

In the pentacene derivatives of Compound Group 9,  $R_2$  and  $R_3$  may be the same or different but are preferably the same substituent as each other.  $R_7$  and  $R_8$  may also be the same or different but are preferably the same substituent as each other. Preferably  $R_2$ ,  $R_3$ ,  $R_7$  and  $R_8$  are the same substituent as each other. Most preferably  $R_2$  and  $R_3$  and  $R_7$  and  $R_8$  together with the carbon atom to which they are attached form a  $C_4$ - $C_{40}$  saturated or unsaturated ring, more preferably a  $C_4$ - $C_{10}$  saturated or unsaturated intervened by one or more oxygen or sulphur atoms or a group represented by the formula  $-N(R_a)$  wherein  $R_a$  is a hydrogen atom or a hydrocarbon group, thereby forming a pseudo-pentacene compound. Preferred pseudo-pentacene derivatives of Compound Group 9 are as shown in Formula 9a and Formula 9b and isomers thereof.



Formula 9a



Formula 9b


In the pseudo-pentacene derivatives of Compound Group 9 preferably  $R_{19}$  and  $R_{20}$  are the same substituent and comprise optionally substituted  $C_{1-40}$  carbyl or hydrocarbyl groups. More preferably  $R_{19}$  and  $R_{20}$  comprise optionally substituted, optionally unsaturated  $C_{1-40}$  carbyl or hydrocarbyl groups, for example, optionally substituted alkyl,

alkenyl, alkynyl, aryl or aralkyl groups or  $R_{19}$  and  $R_{20}$  together with the carbon atoms to which they are attached from an optionally substituted  $C_4$ - $C_{40}$  saturated or unsaturated ring intervened by one or more oxygen or sulphur atoms or a group represented by Formula  $-N(R_a)$  wherein  $R_a$  is a hydrogen atom or a hydrocarbon group. Most preferably the ring (formed by  $R_{19}$  and  $R_{20}$  together with the carbon atoms to which they are attached) is intervened by one or more oxygen atoms. However, it is most preferred that  $R_{19}$  and  $R_{20}$  are the same substituent and comprise hydrogen or a saturated or unsaturated  $C_{1-4}$ -alkyl group for example methyl, ethyl, propyl, or butyl, most preferably  $R_{19}$  and  $R_{20}$  are each independently a methyl group or a hydrogen atom.


In the pseudo pentacene derivatives of compounds 9a and 9b,  $R_{15}$ ,  $R_{16}$ ,  $R_{17}$  may be the same or different, most preferably  $R_{15}$ ,  $R_{16}$  and  $R_{17}$  are the same and are as described in relation to compounds of Formula 8 above.

In the pseudo pentacene derivatives of Compound Group 9 one or more of the ring positions on the compound other than the 2, 3, 5, 7, 8 and 10 positions may be substituted, but preferably the other ring positions are unsubstituted, that is they are occupied by hydrogen.

Examples of Compound Group 9 are given below:



Group 9a, Example 1



Group 9a, Example 2

Preferably, the "R" groups ( $R_1$ ,  $R_2$  etc.) in Compound Groups 1-9 are  $C_{1-40}$  carbyl or hydrocarbyl which may optionally be substituted. Preferably the optional substituent comprises silyl as herein defined below.

In the polyacenes of the present invention (especially Compound Groups 1-9), the  $C_{1-40}$  carbyl or hydrocarbyl group may be a saturated or unsaturated acyclic group, or a saturated or unsaturated cyclic group. Unsaturated acyclic or cyclic groups are preferred, especially alkenyl and alkynyl groups (especially ethynyl). Where the  $C_{1-40}$  carbyl or hydrocarbyl group is acyclic, the group may be linear or branched. The  $C_{1-40}$  carbyl or hydrocarbyl group includes a  $C_{1-40}$  alkyl group, a  $C_{2-40}$  alkenyl group, a  $C_{2-40}$  alkynyl group, a  $C_{3-40}$  allyl group, a  $C_{4-40}$  alkyldienyl group, a  $C_{4-40}$  polyenyl group, a  $C_6-C_{18}$  aryl group, a  $C_6-C_{40}$  alkylaryl group, a  $C_6-C_{40}$  arylalkyl group, a  $C_4-C_{40}$  cycloalkyl group, a  $C_4-C_{40}$  cycloalkenyl group, and the like. Preferred among the foregoing groups are a  $C_1-C_{20}$  alkyl group, a  $C_2-C_{20}$  alkenyl group, a  $C_2-C_{20}$  alkynyl group, a  $C_3-C_{20}$  allyl group, a  $C_4-C_{20}$  alkyldienyl group, a  $C_6-C_{12}$  aryl group and a  $C_4-C_{20}$  polyenyl group, respectively; more preferred are a  $C_1-C_{10}$  alkyl group, a  $C_2-C_{10}$  alkenyl group, a  $C_2-C_{10}$  alkynyl group (especially ethynyl), a  $C_3-C_{10}$  allyl group, a  $C_4-C_{10}$  alkyldienyl group, a  $C_6-C_{12}$  aryl group and a  $C_4-C_{10}$  polyenyl group, respectively; and most preferred is  $C_{2-10}$  alkynyl.

Examples of the alkyl group are, without limitation, methyl, ethyl, propyl, n-butyl, t-butyl, dodecanyl, trifluoromethyl, perfluoro-n-butyl, 2,2,2-trifluoroethyl, benzyl, 2-phenoxyethyl, etc. Examples of the alkynyl group are ethynyl and propynyl. Examples of the aryl group are, without limitation, phenyl, 2-tolyl, 3-tolyl, 4-tolyl, naphthyl, biphenyl, 4-phenoxyphenyl, 4-fluorophenyl, 3-carbomethoxyphenyl, 4-carbomethoxyphenyl, etc. Examples of the alkoxy group are, without limitation, methoxy, ethoxy, 2-methoxyethoxy, t-butoxy, etc. Examples of the aryloxy group are, without limitation, phenoxy, naphthoxy, phenylphenoxy, 4-methylphenoxy, etc. Examples of the amino group are, without limitation, dimethylamino, methylamino, methylphenylamino, phenylamino, etc.

In the polyacenes of the present invention, the optional substituents on the said  $C_{1-40}$  carbyl or hydrocarbyl groups for  $R_1$  etc. preferably are selected from: silyl, sulpho, sulphonyl, formyl, amino, imino, nitrilo, mercapto, cyano, nitro, halo,  $C_{1-4}$  alkyl,  $C_{6-12}$  aryl,  $C_{1-4}$  alkoxy, hydroxy and/or all chemically possible combinations thereof. More preferable among these optional substituents are silyl and  $C_{6-12}$  aryl and most preferable is silyl.

The silyl group in this specification, which may be optionally substituted, may be shown by formula:  $-\text{Si}(\text{R}_{15})(\text{R}_{16})(\text{R}_{17})$ , wherein each of  $\text{R}_{15}$ ,  $\text{R}_{16}$  and  $\text{R}_{17}$ , which may be the same or different, independently represents hydrogen, a  $C_{1-40}$ -alkyl group (preferably  $C_{1-4}$ -alkyl and most preferably methyl, ethyl, n-propyl or isopropyl) which may optionally be substituted e.g. with a halogen atom; a  $C_{6-40}$ -aryl group (preferably phenyl) which may optionally be substituted e.g. with a halogen atom; a  $C_{6-40}$ -arylalkyl group which may optionally be substituted e.g. with a halogen atom; a  $C_{1-40}$ -alkoxy group which may optionally be substituted e.g. with a halogen atom; or a  $C_{6-40}$ -arylalkyloxy group which may optionally be substituted e.g. with a halogen atom. Preferably,  $\text{R}_{15}$ ,  $\text{R}_{16}$  and  $\text{R}_{17}$  are


each independently selected from optionally substituted  $C_{1-10}$ -alkyl (more preferably  $C_{1-4}$  and even more preferably  $C_{1-3}$ -alkyl, e.g. isopropyl) and optionally substituted  $C_{6-10}$ -aryl (preferably phenyl).

In one preferred embodiment of silyl group,  $R_{15}$ ,  $R_{16}$  and  $R_{17}$  are preferably the same group as each other, e.g. the same optionally substituted alkyl group, as in triisopropylsilyl. Preferably, in that preferred embodiment, the groups  $R_{15}$ ,  $R_{16}$  and  $R_{17}$  are the same optionally substituted  $C_{1-10}$  (more preferably  $C_{1-4}$  and even more preferably  $C_{1-3}$ ) alkyl group. A preferred alkyl group in this case is isopropyl.


A silyl group of formula  $-\text{Si}(R_{15})(R_{16})(R_{17})$  as described above is a preferred optional substituent for the  $C_1$ - $C_{40}$ -carbonyl or hydrocarbonyl group etc.

Examples of the silyl group  $-\text{Si}(R_{15})(R_{16})(R_{17})$  are, without limitation, trimethylsilyl, triethylsilyl, tripropylsilyl, dimethylethylsilyl, diethylmethylsilyl, dimethylpropylsilyl, dimethylisopropylsilyl, dipropylmethylsilyl, diisopropylmethylsilyl, dipropylethylsilyl, diisopropylethylsilyl, diethylisopropylsilyl, triisopropylsilyl, trimethoxysilyl, triethoxysilyl, triphenylsilyl, diphenylisopropylsilyl, diisopropylphenylsilyl, diphenylethylsilyl, diethylphenylsilyl, diphenylmethylsilyl, triphenoxysilyl, dimethylmethoxysilyl, dimethylphenoxysilyl, methylmethoxyphenyl, etc. For each example in the foregoing list, the alkyl, aryl or alkoxy group may optionally be substituted.

Most preferred pentacene compounds of the invention are those of Compound Groups 1, 2, 8 and 9. Preferred among Compound Groups 1 and 2 are compounds of Formula 1A or 2A (especially Formula 1A):




Formula 1A




Formula 2A

wherein each R' is independently selected from a C<sub>2-40</sub> alkyl group, a C<sub>2-40</sub> alkoxy group, a C<sub>2-40</sub> alkenyl group, C<sub>2-40</sub> alkynyl group, a C<sub>6-18</sub> aryl or heteroaryl group, C<sub>6-40</sub> aryloxy group, C<sub>7-40</sub> alkylaryloxy group, a C<sub>2-40</sub> alkoxycarbonyl group, a C<sub>7-40</sub> aryloxycarbonyl group, or a silyl group, each of which may be optionally substituted, or a cyano group (-CN), a carbamoyl group (-C(=O)NH<sub>2</sub>), a haloformyl group (-C(=O)-X, wherein X represents a halogen atom), a formyl group (-C(=O)-H), an isocyano group, an isocyanate group, a thiocyanate group or a thioisocyanate group, an optionally substituted amino group, an imino group, a hydroxy group, a halo, a sulpho group, a sulphonyl group a mercapto group, or a nitro group. Preferably, in Formulae 1A and 2A, each R' is independently selected from C<sub>6-18</sub> aryl and silyl, which may both optionally be substituted. Preferably in Formula 1A or 2A, at least one R' and most preferably both R' is silyl, wherein the silyl group is preferably defined as above, that is, a silyl group of formula -Si(R<sub>15</sub>)(R<sub>16</sub>)(R<sub>17</sub>). These latter highly preferred compounds thus have Formulae 1B and 2B:



Formula 1B



Formula 2B

Examples of compounds of Formulae 1B and 2B include, without limitation:

- 6,13-bis(trimethylsilylethynyl)pentacene
- 6,13-bis(triethylsilylethynyl)pentacene
- 6,13-bis(tripropylsilylethynyl)pentacene
- 5 6,13-bis(dimethylethylsilylethynyl)pentacene
- 6,13-bis(diethylmethylsilylethynyl)pentacene
- 6,13-bis(dimethylpropylsilylethynyl)pentacene
- 6,13-bis(dimethylisopropylsilylethynyl)pentacene
- 6,13-bis(dipropylmethylsilylethynyl)pentacene
- 10 6,13-bis(diisopropylmethylsilylethynyl)pentacene
- 6,13-bis(dipropylethylsilylethynyl)pentacene
- 6,13-bis(diisopropylethylsilylethynyl)pentacene
- 6,13-bis(diethylisopropylsilylethynyl)pentacene
- 6,13-bis(triisopropylsilylethynyl)pentacene
- 15 6,13-bis(trimethoxysilylethynyl)pentacene
- 6,13-bis(triethoxysilylethynyl)pentacene
- 6,13-bis(triphenylsilylethynyl)pentacene
- 6,13-bis(diphenylisopropylsilylethynyl)pentacene
- 6,13-bis(diisopropylphenylsilylethynyl)pentacene
- 20 6,13-bis(diphenylethylsilylethynyl)pentacene
- 6,13-bis(diethylphenylsilylethynyl)pentacene
- 6,13-bis(diphenylmethylsilylethynyl)pentacene
- 6,13-bis(triphenoxysilylethynyl)pentacene
- 6,13-bis(dimethylmethoxysilylethynyl)pentacene
- 25 6,13-bis(dimethylphenoxysilylethynyl)pentacene
- 6,13-bis(methylmethoxyphenylethynyl)pentacene
- 6,13-bis(cyclopentamethylenesilane)pentacene
- 6,13-bis(cyclotetramethylenesilane)pentacene
- 5,14-bis(trimethylsilylethynyl)pentacene
- 30 5,14-bis(triethylsilylethynyl)pentacene
- 5,14-bis(tripropylsilylethynyl)pentacene
- 5,14-bis(dimethylethylsilylethynyl)pentacene
- 5,14-bis(diethylmethylsilylethynyl)pentacene
- 5,14-bis(dimethylpropylsilylethynyl)pentacene
- 35 5,14-bis(dimethylisopropylsilylethynyl)pentacene
- 5,14-bis(dipropylmethylsilylethynyl)pentacene
- 5,14-bis(diisopropylmethylsilylethynyl)pentacene
- 5,14-bis(dipropylethylsilylethynyl)pentacene
- 5,14-bis(diisopropylethylsilylethynyl)pentacene
- 40 5,14-bis(diethylisopropylsilylethynyl)pentacene



5,14-bis(triisopropylsilylethynyl)pentacene

5,14-bis(trimethoxysilylethynyl)pentacene

5,14-bis(triethoxysilylethynyl)pentacene

5,14-bis(triphenylsilylethynyl)pentacene

5 5,14-bis(diphenylisopropylsilylethynyl)pentacene

5,14-bis(diisopropylphenylsilylethynyl)pentacene

5,14-bis(diphenylethylsilylethynyl)pentacene

5,14-bis(diethylphenylsilylethynyl)pentacene

5,14-bis(diphenylmethylsilylethynyl)pentacene

10 5,14-bis(triphenoxysilylethynyl)pentacene

5,14-bis(dimethylmethoxysilylethynyl)pentacene

5,14-bis(dimethylphenoxysilylethynyl)pentacene


5,14-bis(methylmethoxyphenylethynyl)pentacene

15 In one type of preferred embodiment,  $R_{15}$ ,  $R_{16}$  and  $R_{17}$  in Formulae 1B and 2B are preferably the same as each other, for example the same alkyl group, as in the preferred examples of 6,13-bis-(triisopropylsilylethynyl)pentacene and 5,14-bis-(triisopropylsilylethynyl)pentacene. In this particular preferred embodiment,  $R_{15}$ ,  $R_{16}$  and  $R_{17}$  are preferably the same  $C_{1-10}$  (preferably  $C_{1-4}$  and more preferably  $C_{1-3}$ ) alkyl group which may optionally be substituted. Optionally substituted isopropyl is a preferred alkyl group for such embodiments.


20 In some cases it may be desirable to control the solubility of the polyacene in common organic solvents in order to make devices easier to fabricate. This may have advantages in making an FET for example, where solution coating, say, a dielectric onto the polyacene layer may have a tendency to dissolve the polyacene. Also, once a device is formed, a less soluble polyacene may have less tendency to "bleed" across organic layers. In one preferred embodiment, in order to control solubility of the pentacene derivatives of Formulae 1B and 2B above, at least one of  $R_{15}$ ,  $R_{16}$  and  $R_{17}$  contains an optionally substituted aryl (preferably phenyl) group. Thus, at least one of  $R_{15}$ ,  $R_{16}$  and  $R_{17}$  may be an optionally substituted  $C_{6-18}$  aryl (preferably phenyl) group, an optionally substituted  $C_{6-18}$  aryloxy (preferably phenoxy) group, an optionally substituted  $C_{6-20}$  arylalkyl (for example benzyl) group, or an optionally substituted  $C_{6-20}$  arylalkyloxy (for example benzyloxy) group. In such cases, the remaining groups, if any, among  $R_{15}$ ,  $R_{16}$  and  $R_{17}$  are preferably  $C_{1-10}$  (more preferably  $C_{1-4}$ ) alkyl groups which may be optionally substituted. Examples of such preferred embodiments of compounds are given below:

25 30 35 with Formulae 1C and 2C, wherein Ar represents an aryl-containing group for example an optionally substituted  $C_{6-18}$  aryl group, an optionally substituted  $C_{6-18}$  aryloxy group, an optionally substituted  $C_{6-20}$  arylalkyl group or an optionally substituted  $C_{6-20}$  arylalkyloxy group:

23



Formula 1C



Formula 2C

In the Formulae 1C and 2C,  $R_{15}$  and  $R_{17}$  are preferably the same group as each other, for example an isopropyl group. Compounds of Formulae 1C and 2C are believed to be novel and are claimed per se. Additionally, many of the other substituted polyacene compounds disclosed in this specification for use in the present invention are also believed to be novel and, as such, are also claimed per se.

Examples of compounds of Formulae 1C and 2C include, without limitation:

- 6,13-bis(triphenylsilylethynyl)pentacene
- 6,13-bis(diphenylisopropylsilylethynyl)pentacene
- 6,13-bis(diisopropylphenylsilylethynyl)pentacene
- 6,13-bis(diphenylethylsilylethynyl)pentacene
- 6,13-bis(diethylphenylsilylethynyl)pentacene
- 6,13-bis(diphenylmethylsilylethynyl)pentacene
- 6,13-bis(triphenoxysilylethynyl)pentacene
- 6,13-bis(dimethylphenoxysilylethynyl)pentacene
- 6,13-bis(methylmethoxyphenylethynyl)pentacene

5,14-bis(triphenylsilylethynyl)pentacene

5,14-bis(diphenylisopropylsilylethynyl)pentacene

5,14-bis(diisopropylphenylsilylethynyl)pentacene

5,14-bis(diphenylethylsilylethynyl)pentacene

5 5,14-bis(diethylphenylsilylethynyl)pentacene

5,14-bis(diphenylmethylsilylethynyl)pentacene


5,14-bis(triphenoxysilylethynyl)pentacene

5,14-bis(dimethylphenoxysilylethynyl)pentacene

5,14-bis(methylmethoxyphenylethynyl)pentacene

10 In one embodiment of the preferred pentacene compounds of Group 9 one or more of the carbon atoms of the polyacene skeleton may be substituted by a heteroatom selected from N, P, As, O, S, Se and Te, preferably N. An example of such a compound as described in Compound Group 9, wherein two of the carbon atoms of the pentacene skeleton have been substituted by N, is given below:


15



Formula 9a

20 In one embodiment, any two or more of the substituents which are located on adjacent ring positions of the polyacene may, together, optionally constitute a further aromatic ring system fused to the polyacene as described in relation to Compound Group 8. An example of a preferred pentacene compound of Group 8 is given below wherein each pair of adjacent substituents  $R_1$  and  $R_2$ ,  $R_3$  and  $R_4$ ,  $R_5$  and  $R_6$ , and  $R_{10}$  and  $R_{11}$  constitute a benzene ring fused to the pentacene:

25



Formula 8a

Additional examples of preferred compounds of Group 8 and Group 9 are as previously illustrated under the general description of each group.

In a preferred embodiment the semiconducting polyacene has a field effect mobility,  $\mu$ , of more than  $10^{-5} \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$ , preferably of more than  $10^{-4} \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$ , more preferably of more than  $10^{-3} \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$ , still more preferably of more than  $10^{-2} \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$  and most preferably of more than  $10^{-1} \text{ cm}^2\text{V}^{-1}\text{s}^{-1}$ .

The organic binder resin, which is a polymer, may be referred to herein as the organic binder or simply the binder.

Preferred binders are materials of low permittivity, that is those having a permittivity,  $\epsilon$ , at 1,000 Hz of 3.3 or less. However, binders of higher permittivity may be used. The organic binder preferably has a permittivity at 1,000 Hz of less than 3.0, more preferably 2.8 or less. Preferably the organic binder has a permittivity at 1,000 Hz greater than 1.7, especially a permittivity from 2.0 to 2.8.

An example of a suitable organic binder is polystyrene. Further examples are given below.

In one type of preferred embodiment, the organic binder is one in which at least 95%, more preferably at least 98% and especially all of the atoms consist of hydrogen, fluorine and carbon atoms.

It is preferred that the binder normally contains conjugated bonds especially conjugated double bonds and/or aromatic rings.

The binder should preferably be capable of forming a film, more preferably a flexible film. Copolymers of styrene and alpha methyl styrene, for example copolymers of styrene, alpha methyl styrene and butadiene may suitably be used.

Binders of low permittivity of use in the present invention have few permanent dipoles which could otherwise lead to random fluctuations in molecular site energies. The permittivity (dielectric constant) can be determined by the ASTM D150 test method.

It is desirable that the permittivity of the binder has little dependence on frequency. This is typical of non-polar materials. Polymers and/or copolymers can be chosen as the

binder by the permittivity of their substituent groups. A list of low polarity binders suitable for use in the present invention is given (without limiting to these examples) in Table 1 :

Table 1

Binder	typical low frequency - permittivity $\epsilon$
Polystyrene	2.5
poly( $\alpha$ -methylstyrene)	2.6
poly( $\alpha$ -vinyl naphthalene)	2.6
poly(vinyltoluene)	2.6
Polyethylene	2.2-2.3
cis-polybutadiene	2.0
Polypropylene	2.2
Polyisoprene	2.3
poly(4-methyl-1-pentene)	2.1
poly(tetrafluoroethylene)	2.1
poly(chlorotrifluoroethylene)	2.3-2.8
poly(2-methyl-1,3-butadiene)	2.4
poly(p-xylylene)	2.6
poly( $\alpha$ - $\alpha$ '- $\alpha$ '- $\alpha$ ' tetrafluoro-p-xylylene)	2.4
poly[1,1-(2-methyl propane)bis(4-phenyl)carbonate]	2.3
poly(cyclohexyl methacrylate)	2.5
poly(chlorostyrene)	2.6
poly(2,6-dimethyl-1,4-phenylene ether)	2.6
Polyisobutylene	2.2
poly(vinyl cyclohexane)	2.2

Other polymers suitable as binders include poly(4-methylstyrene), poly(1,3-butadiene) or polyphenylene. Copolymers containing the repeat units of the above polymers are also suitable as binders. Copolymers offer the possibility of improving compatibility with the polyacene, modifying the morphology and/or the glass transition temperature of the final layer composition. It will be appreciated that in the above table certain materials are insoluble in commonly used solvents for preparing the layer. In these cases analogues can be used as copolymers. Some examples of copolymers are given in Table 2 (without limiting to these examples). Both random or block copolymers can be used. It is also possible to add some more polar monomer components as long as

the overall composition remains low in polarity.

Table 2

Binder	typical low frequency permittivity ( $\epsilon$ )
poly(ethylene/tetrafluoroethylene)	2.6
poly(ethylene/chlorotrifluoroethylene)	2.3
fluorinated ethylene/propylene copolymer	2-2.5
polystyrene-co- $\alpha$ -methylstyrene	2.5-2.6
ethylene/ethyl acrylate copolymer	2.8
poly(styrene/10%butadiene)	2.6
poly(styrene/15%butadiene)	2.6
poly(styrene/2,4 dimethylstyrene)	2.5

5


Other copolymers may include branched or non-branched polystyrene-block-polybutadiene, polystyrene-block(polyethylene-ran-butylene)-block-polystyrene, polystyrene-block-polybutadiene-block-polystyrene, polystyrene-(ethylene-propylene)-diblock-copolymers (e.g. KRATON®-G1701E, Shell), poly(propylene-co-ethylene) and poly(styrene-co-methylmethacrylate).

0

The organic binder itself may be a semiconductor, where it will be referred to herein as a semiconducting binder. The semiconducting binder is still preferably a binder of low permittivity as herein defined. The semiconducting binder preferably has a number average molecular weight ( $M_n$ ) of at least 2000, more preferably at least 3000, even more preferably at least 4000 and most preferably at least 5000. The semiconducting binder preferably has a charge carrier mobility,  $\mu$ , of at least  $10^{-5} \text{ cm}^2/\text{V.s}$ , more preferably at least  $10^{-4} \text{ cm}^2/\text{V.s}$ .

5

A preferred class of semiconducting binder has repeat units of a Formula 10:




Formula 10

20


wherein  $\text{Ar}^1$ ,  $\text{Ar}^2$  and  $\text{Ar}^3$ , which may be the same or different, each represent independently if in different repeat units, an optionally substituted aromatic group (mononuclear or polynuclear) and in the resin  $n$  is an integer of at least 5, preferably at least 10, more preferably at least 15 and most preferably at least 20. In the context of  $\text{Ar}^1$ ,

Ar<sup>2</sup> and Ar<sup>3</sup>, a mononuclear aromatic group has only one aromatic ring, for example phenyl or phenylene. A polynuclear aromatic group has two or more aromatic rings which may be fused (for example naphthyl or naphthylene), individually covalently linked (for example biphenyl) and/or a combination of both fused and individually linked aromatic rings. Preferably each Ar<sup>1</sup>, Ar<sup>2</sup> and Ar<sup>3</sup> is an aromatic group which is substantially conjugated over substantially the whole group.

Preferred classes of semiconducting binders are those containing substantially conjugated repeat units. The semiconducting polymer may be a homopolymer or copolymer (including a block-copolymer) of the general Formula 11:




where A, B,...,Z each represent a monomer unit and (c), (d),...(z) each represent the fraction of the respective monomer unit in the polymer, that is each (c), (d),...(z) is a value from 0 to 1 and the total of (c) + (d) +...+ (z) = 1. Examples of monomer units A, B,...,Z include units of Formula 10 and Formulae 12-17 given below:



Formula 12


where R1 and R2 may be independently H; optionally substituted alkyl; alkoxy; thioalkyl; acyl; optionally substituted aryl; a fluorine atom; a cyano group; a nitro group; an optionally substituted secondary or tertiary alkylamine or arylamine -N(R<sub>a</sub>)(R<sub>b</sub>), where R<sub>a</sub> and R<sub>b</sub> may each be independently represented by H, alkyl, substituted alkyl, aryl, substituted aryl, alkoxy or polyalkoxy groups; or other substituent and \* is any terminal or end capping group including hydrogen (the alkyl and aryl groups may be optionally fluorinated);



Formula 13

in which X may be Se, Te, O, S or -N(R) preferably O, S or -N(R)-, where R represents H, alkyl, substituted alkyl, aryl, or substituted aryl; R1 and R2 are as for formula 12;


29



Formula 14

in which X is as for Formula 13, and R1 and R2 are as for Formula 12;


5



Formula 15

10


in which X is as for Formula 13; R1, R2 are as for Formula 12; and Z represents -C(T<sub>1</sub>)=C(T<sub>2</sub>)-, -C≡C-, -N(R')-, -N=N-, (R')=N-, -N=C(R')-, wherein T<sub>1</sub> and T<sub>2</sub> independently represent -H, Cl, F, -C≡N or a lower alkyl and R' represents -H, alkyl, substituted alkyl, aryl, or substituted aryl;



Formula 16

15

where R1 and R2 are as for Formula 12;



Formula 17

20

where R1-R4 may be independently selected from the same list of groups as for R1 and R2 in Formula 12.

25

In the case of polymeric Formulae herein, such as formulae 10-17, the polymers may be terminated by any terminal group, that is any end-capping or leaving group, including hydrogen.



In the case of a block-copolymer, each monomer A, B, ... Z may be a conjugated oligomer or polymer comprising a number, for example 2 to 50, of the units of Formulae 12-17. The semiconducting binder preferably includes arylamine, fluorene, thiophene, spiro bifluorene and/or optionally substituted aryl (e.g. phenylene) groups, more preferably arylamine, still more preferably triarylamine. The aforementioned groups may be linked by further conjugating groups for example vinylene. Additionally preferably the semiconducting binder comprises a polymer (either a homo-polymer or copolymer, including block-copolymer) containing one or more of the aforementioned arylamine, fluorene, thiophene and/or optionally substituted aryl groups. A preferred semiconducting binder comprises a homo-polymer or copolymer (including block-copolymer) containing arylamine (preferably triarylamine) and/or fluorene units. Another preferred semiconducting binder comprises a homo-polymer or co-polymer (including block-copolymer) containing fluorene and/or thiophene units.

The semiconducting binder may also contain carbazole, stilbene repeat units. For example polyvinylcarbazole or polystilbene polymers, copolymers may be used. The semiconducting binder may optionally contain polyacene segments (for example repeat units as formula A above) to improve compatibility with the soluble polyacene molecules.

For application of the semiconducting layer of the invention in p-channel FETs, it is desirable that the binder should have a higher ionisation potential than the polyacene semiconductor, otherwise the binder may form hole traps. In n-channel materials the binder should have lower electron affinity than the n-type semiconductor to avoid electron trapping.

The formulation according to the invention may be prepared by a process which comprises first mixing both the polyacene compound and the organic binder, preferably the mixing comprises mixing the two components together in a solvent or solvent mixture. The solvent may be a single solvent or the polyacene compound and the organic binder may each be dissolved in a separate solvent followed by mixing the two resultant solutions to mix the compounds. The solvent(s) containing the polyacene compound and the organic binder may then be applied to a substrate. The solvent(s) may be evaporated to form the layer of the invention.

The binder may be formed *in situ* by mixing or dissolving the polyacene in a precursor of the binder, for example a liquid monomer, oligomer or crosslinkable polymer, optionally in the presence of a solvent, and depositing the mixture or solution, for example by dipping, spraying, painting or printing it, on a substrate to form a liquid layer and then curing the liquid monomer, oligomer or crosslinkable polymer, for example by exposure to radiation, heat or electron beams, to produce a solid layer.

If a preformed binder is used it may be dissolved together with the polyacene in a suitable solvent, and the solution deposited for example by dipping, spraying, painting or printing it on a substrate to form a liquid layer and then removing the solvent to leave a solid layer. Suitable solvents are chosen from those classes which are a good solvent for

both the binder and polyacene, and which upon evaporation from the solution blend give a coherent defect free layer. Suitable solvents for the binder or polyacene can be determined by preparing a contour diagram for the material as described in ASTM Method D 3132 at the concentration at which the mixture will be employed. The material is added to a wide variety of solvents as described in the ASTM method. Examples of organic solvents which may be considered are:  $\text{CH}_2\text{Cl}_2$ ,  $\text{CHCl}_3$ , monochlorobenzene, o-dichlorobenzene, tetrahydrofuran, anisole, morpholine, toluene, o-xylene, m-xylene, p-xylene, 1,4-dioxane, acetone, methylethylketone, 1,2-dichloroethane, 1,1,1-trichloroethane, 1,1,2,2-tetrachloroethane, ethyl acetate, n-butyl acetate, dimethylformamide, dimethylacetamide, dimethylsulfoxide, tetralin, decalin and/or mixtures thereof. After the appropriate mixing and ageing, solutions are evaluated as one of the following categories: complete solution, borderline solution or insoluble. The contour line is drawn to outline the solubility parameter-hydrogen bonding limits dividing solubility and insolubility. 'Complete' solvents falling within the solubility area can be chosen from literature values such as published in "Crowley, J.D., Teague, G.S. Jr and Lowe, J.W. Jr., Journal of Paint Technology, 38, No 496, 296 (1966)". Solvent blends may also be used and can be identified as described in "Solvents, W.H.Ellis, Federation of Societies for Coatings Technology, p9-10, 1986". Such a procedure may lead to a blend of 'non' solvents that will dissolve both the binder and polyacene, although it is desirable to have at least one true solvent in a blend.

The proportions of the binder to the polyacene in the formulation or layer according to the present invention are typically 20:1 to 1:20, preferably 10:1 to 1:10 more preferably 5:1 to 1:5, still more preferably 3:1 to 1:3 and most preferably 2:1 to 1:2 (e.g. about 1:1). Surprisingly and beneficially, dilution of the polyacene in the binder has been found to have little or no effect on the charge mobility, in contrast to what would have been expected from the prior art.

It is desirable to generate small structures in modern microelectronics to reduce cost (more devices/unit area), and power consumption. Patterning of the layer of the invention may be carried out by photolithography or electron beam lithography.

Liquid coating of organic electronic devices such as field effect transistors is more desirable than vacuum deposition techniques. The polyacene and binder mixtures of the present invention enable the use of a number of liquid coating techniques. The organic semiconductor layer may be incorporated into the final device structure by, for example and without limitation, dip coating, spin coating, ink jet printing, letter-press printing, screen printing, doctor blade coating; roller printing, reverse-roller printing; offset lithography printing, flexographic printing, web printing, spray coating, brush coating or pad printing.

Selected polyacene and binder compositions of the present invention may be applied to prefabricated device substrates by ink jet printing or microdispensing. Preferably industrial piezoelectric print heads such as but not limited to those supplied by

Aprion, Hitachi-Koki, InkJet Technology, On Target Technology, Picojet, Spectra, Trident, Xaar may be used to apply the organic semiconductor layer to a substrate. Additionally semi-industrial heads such as those manufactured by Brother, Epson, Konica, Seiko Instruments Toshiba TEC or single nozzle microdispensers such as those produced by Microdrop and Microfab may be used.

In order to be applied by ink jet printing or microdispensing, polyacene and binder compositions must first be dissolved in a suitable solvent. Solvents must fulfill the requirements stated above and must not have any detrimental effect on the chosen print head. Additionally, solvents should have boiling points  $>100^{\circ}\text{C}$ , preferably  $>140^{\circ}\text{C}$  and more preferably  $>150^{\circ}\text{C}$  in order to prevent operability problems caused by the solution drying out inside the print head. Suitable solvents include substituted and non-substituted xylene derivatives, di- $\text{C}_{1-2}$ -alkyl formamide, substituted and non-substituted anisoles and other phenol-ether derivatives, substituted heterocycles such as substituted pyridines, pyrazines, pyrimidines, pyrrolidinones, substituted and non-substituted  $N,N$ -di- $\text{C}_{1-2}$ -alkylanilines and other fluorinated or chlorinated aromatics.

A preferred solvent for depositing the binder/polyacene formulation by ink jet printing comprises a benzene derivative which has a benzene ring substituted by one or more substituents wherein the total number of carbon atoms among the one or more substituents is at least three. For example, the benzene derivative may be substituted with a propyl group or three methyl groups, in either case there being at least three carbon atoms in total. Such a solvent enables an ink jet fluid to be formed comprising the solvent with the binder and polyacene which reduces or prevents clogging of the jets and separation of the components during spraying. The solvent(s) may include those selected from the following list of examples: dodecylbenzene; 1-Methyl-4-tert-butylbenzene; Terpeneol; Limonene; Isodurene; Terpinolene; Cymene; Diethylbenzene. The solvent may be a solvent mixture, that is a combination of two or more solvents, each solvent preferably having a boiling point  $>100^{\circ}\text{C}$ , more preferably  $>140^{\circ}\text{C}$ . Such solvent(s) also enhance film formation in the layer deposited and reduce defects in the layer.

The ink jet fluid (that is mixture of solvent, binder and polyacene) preferably has a viscosity at  $20^{\circ}\text{C}$  of 1-100mPa.s, more preferably 1-50mPa.s and most preferably 1-30mPa.s

The use of the binder in the present invention also allows the viscosity of the coating solution to be tuned to meet the requirements of the particular print head.

The semiconducting layer of the present invention is typically at most 1 micron ( $=1\mu\text{m}$ ) thick, although it may be thicker if required. The exact thickness of the layer will depend, for example, upon the requirements of the electronic device in which the layer is used. For use in an OFET or OLED, the layer thickness may typically be 500 nm or less.

In the semiconducting layer of the present invention there may be used two or more different polyacene compounds of Formula 1-9. Additionally or alternatively, in the semiconducting layer there may be used two or more organic binder resins of the present

invention.

As mentioned above, the invention further provides a process for preparing the organic semiconducting layer which comprises (i) depositing on a substrate a liquid layer of a mixture which comprises the polyacene compound, the organic binder resin or precursor thereof and optionally a solvent, and (ii) forming from the liquid layer a solid layer which is the organic semiconducting layer.

In the process, the solid layer may be formed by evaporation of the solvent and/or by reacting the binder resin precursor (if present) to form the binder resin *in situ*. The substrate may include any underlying device layer, electrode or separate substrate such as silicon wafer or polymer substrate for example.

In one particular embodiment of the present invention, the binder may be alignable, for example capable of forming a liquid crystalline phase. In that case the binder may assist alignment of the polyacene, for example such that the polyacene backbone is preferentially aligned along the direction of charge transport. Suitable processes for aligning the binder include those processes used to align polymeric organic semiconductors such as described in WO 03/007397 (Plastic Logic).

The present invention also provides the use of the semiconducting formulation or layer in an electronic device. The formulation may be used as a high mobility semiconducting material in various devices and apparatus. The formulation may be used, for example, in the form of a semiconducting layer or film. Accordingly, in another aspect, the present invention provides a semiconducting layer for use in an electronic device, the layer comprising the formulation according to the invention. The layer or film may be less than about thirty microns. For various electronic device applications, the thickness may be less than about one micron thick. The layer may be deposited, for example on a part of an electronic device, by any of the aforementioned solution coating or printing techniques.

The formulation may be used, for example as a layer or film, in a field effect transistor (FET) for example as the semiconducting channel, organic light emitting diode (OLED) for example as a hole or electron injection or transport layer or electroluminescent layer, photodetector, chemical detector, photovoltaic cell (PVs), capacitor sensor, logic circuit, display, memory device and the like. The formulation may also be used in electrophotographic (EP) apparatus, for example in the organic photoconductor. The formulation is preferably solution coated to form a layer or film in the aforementioned devices or apparatus to provide advantages in cost and versatility of manufacture. The improved charge carrier mobility of the formulation of the present invention enables such devices or apparatus to operate faster and/or more efficiently. The formulation and layer of the present invention are especially suitable for use in an OFET as the semiconducting channel. Accordingly, the invention also provides an organic field effect transistor (OFET) comprising a source electrode, a drain electrode and an organic semiconducting channel connecting the source and drain electrodes, wherein the organic semiconducting channel

comprises a layer according to the present invention. Other features of the OFET are well known to those skilled in the art.

Some definitions and explanations of terms used herein are now given.

When in the formulae herein there is a list of labels (for example  $R_1$ ,  $R_2$  etc.) or indices (for example 'n') which are said to represent a list of groups or numerical values, and these are said to be "independent in each case" this indicates each label and/or index can represent any of those groups listed independently from each other, independently within each repeat unit, independently within each Formula and/or independently on each group which is substituted as appropriate. Thus, in each of these instances, many different groups might be represented by a single label (for example  $R_5$ ).

The terms 'substituent', 'substituted', 'optional substituent' and/or 'optionally substituted' as used herein (unless followed by a list of other substituents) signifies at least one of the following groups (or substitution by these groups): silyl, sulpo, sulphonyl, formyl, amino, imino, nitrilo, mercapto, cyano, nitro, halo,  $C_{1-4}$ alkyl,  $C_{6-12}$  aryl,  $C_{1-4}$ alkoxy, hydroxy and/or combinations thereof. These optional groups may comprise all chemically possible combinations in the same group and/or a plurality (preferably two) of the aforementioned groups (for example amino and sulphonyl if directly attached to each other represent a sulphamoyl radical). Preferred optional substituents comprise:  $C_{1-4}$ alkyl; methoxy and/or ethoxy (any of these optionally substituted by at least one halo); amino (optionally substituted by at least one methyl and/or ethyl); and/or halo.

The term 'carbonyl group' as used herein denotes any monovalent or multivalent organic radical moiety which comprises at least one carbon atom either without any non-carbon atoms (for example  $-C\equiv C-$ ), or optionally combined with at least one other non-carbon atom (for example alkoxy, carbonyl etc.).

The term 'hydrocarbon group', 'hydrocarbonyl' or the like may be used herein interchangeably. A hydrocarbon group may be optionally substituted. A hydrocarbon group may also contain at least one of the following heteroatom containing moieties: oxy, thio, sulphinyl, sulphonyl, amino, imino, nitrilo and/or combinations thereof.

The terms 'alkyl', 'aryl', etc. as used herein may be readily replaced, where appropriate, by terms denoting a different degree of valence for example multivalent species (for example alkylene, arylene, etc.).

The term 'halo' as used herein signifies fluoro, chloro, bromo and iodo.

Unless the context clearly indicates otherwise, a group herein which comprises a chain of three or more carbon atoms signifies a group in which the chain wholly or in part may be linear, branched and/or form a ring (including spiro and/or fused rings).

Unless the context clearly indicates otherwise, as used herein plural forms of the terms herein are to be construed as including the singular form and vice versa.

Throughout the description and claims of this specification, the words "comprise" and "contain" and variations of the words, for example "comprising" and "comprises", mean "including but not limited to", and are not intended to (and do not) exclude other


components.

It will be appreciated that variations to the foregoing embodiments of the invention can be made while still falling within the scope of the invention. Each feature disclosed in this specification, unless stated otherwise, may be replaced by alternative features serving the same, equivalent or similar purpose. Thus, unless stated otherwise, each feature disclosed is one example only of a generic series of equivalent or similar features.

All of the features disclosed in this specification may be combined in any combination, except combinations where at least some of such features and/or steps are mutually exclusive. In particular, the preferred features of the invention are applicable to all aspects of the invention and may be used in any combination. Likewise, features described in non-essential combinations may be used separately (not in combination).

It will be appreciated that many of the features described above, particularly of the preferred embodiments, are inventive in their own right and not just as part of an embodiment of the present invention. Independent protection may be sought for these features in addition to or alternative to any invention presently claimed.

The invention will now be described in more detail by reference to the following examples, which are illustrative only and do not limit the scope of the invention.

ExamplesSynthesis of organic semiconductor materials5 1. Synthesis of 6, 13-bis(triisopropylsilyl)ethynyl)pentacene - Formula B (TIPS)

Formula B (TIPS)


10 To a flame-dried flask fitted with mechanical stirrer, nitrogen inlet and outlet, condenser and suba-seal was added isopropylmagnesium chloride (2M in THF (10 molar equivalents based on 6, 13-pentacenequinone)). This solution was cooled using a cold-water bath to act as a cold trap to absorb any exotherm during the triisopropylsilyl acetylene addition.

15 Triisopropylsilyl acetylene (10.1 molar equivalents based on 6, 13-pentacenequinone) was added to the reaction flask drop-wise over 30 minutes followed by the addition of THF (10ml for every 10mmol of TIPS acetylene). The cold-water bath was removed and the solution heated at 60°C for 20 minutes. The flask was then allowed to cool to room temperature. 6, 13-Pentacenequinone (1 molar equivalent) was added to the Grignard reagent and the resulting cloudy suspension was heated at 60°C until the reaction was deemed complete according to HPLC, (up to 3 hours). The flask was allowed to cool to

20 room temperature. A solution of 10% aqueous HCl saturated with tin (II) chloride was added cautiously to the brown / red reaction solution until the solution no longer exothermed on addition. (It was noted that as the tin (II) chloride solution was added, the reaction solution turned from brown / red to a deep blue colour). The resulting solution was heated at 60°C for 30 minutes before cooling to room temperature. This crude

mixture was isolated from a water / DCM mixture drying the organic phase over  $\text{MgSO}_4$  before filtering and concentrating under vacuum to give a blue / black solid. Purification by column chromatography (silica gel, 5% DCM in hexane) followed by recrystallisation from acetone yielded the title compound as dark blue plates.


2(a). Synthesis of 4,5-dimethylphthalaldehyde - Formula C



Formula C

To a solution of oxalyl chloride 2M in dichloromethane (DCM) (26.5mL, 53.0mmol, 2.2 molar equivalents) cooled to  $-78^\circ\text{C}$  was added dropwise a solution of dimethylsulfoxide (DMSO) (7.5mL, 105.8mmol, 4.4 molar equivalents) in DCM (10ml). The solution was stirred at  $-78^\circ\text{C}$  for 5 min and 4,5-dimethylbenzene-1,2-dimethanol (4.0g, 24.1mmol, 1.0 molar equivalent) dissolved in a mixture of DCM-DMSO (2ml-4ml) was added dropwise. The solution was stirred for 1h at  $-78^\circ\text{C}$  and triethylamine (20mL) was slowly added at  $-78^\circ\text{C}$ . The reaction mixture was stirred for 10 minutes at  $-78^\circ\text{C}$  and slowly warmed up to room temperature. Ice-cold water (100ml) was added to the reaction mixture and the aqueous layer extracted with DCM (3x100ml). The organic fractions were combined, dried over magnesium sulfate, filtered and concentrated *in vacuum* to give a brown oil. Purification by column chromatography on silica gel (eluent: hexane-ethyl acetate 8/2) gave the title compound as white needles (3.2 g, 82%).  $^1\text{H}$  NMR (300.13 MHz,  $\text{CDCl}_3$ )  $\delta$ (ppm) 2.42 (s, 6H) 7.73 (s, 2H) 10.50 (s, 2H).

2(b). Synthesis of 2,3,9,10-tetramethyl-6,13-pentacenequinone - Formula D




Formula D

To a solution of 4,5-dimethylphthalaldehyde (Formula C) (1.59g, 9.8mmol, 2 molar equivalents) and 1,4-cyclohexanedione (0.54g, 4.8mmol, 1 molar equivalent) in ethanol (150ml) was added a solution of 5% aqueous NaOH (3ml) at room temperature. The reaction mixture was stirred for 30 minutes at room temperature and then warmed to  $60^\circ\text{C}$ . After 1 hour at  $60^\circ\text{C}$ , the reaction mixture was cooled to room temperature. The resulting



precipitate was filtered, washed with water (25ml), ethanol (50ml) and diethyl ether (50ml) to give the title compound as a yellow powder (1.63g, 93%). IR (selected bands) 1672 (quinone), 1579, 1452, 1396, 1221, 738  $\text{cm}^{-1}$ .



5 3. Synthesis of 2,3,9,10-tetramethyl-6,13-bis(triisopropylsilyl)ethynylpentacene - Formula E



10 Formula E



To a solution of triisopropylsilylacetylene (3.7mL, 16.4mmol, 6 molar equivalents) in tetrahydrofuran (THF) (100ml) cooled to  $-78^{\circ}\text{C}$  was added dropwise a 2.5M solution of *n*-butyllithium in hexane (6mL, 15mmol, 5.5 molar equivalents). The solution was stirred at  $-78^{\circ}\text{C}$  for 45 minutes and 2,3,9,10-tetramethyl-6,13-pentacenequinone (Formula D) (1g, 2.7mmol, 1 molar equivalent) was added. The reaction mixture was warmed up and stirred overnight at room temperature. A solution of 10% aqueous HCl saturated with  $\text{SnCl}_2$  (10ml) was added at room temperature and the reaction mixture was stirred at  $50^{\circ}\text{C}$  for 45 minutes. On cooling a solution of 2M aqueous solution of  $\text{Na}_2\text{CO}_3$  (10ml) was added and the resulting solution stirred with celite for 5 minutes. The solution was filtered through celite and concentrated under vacuum to give a dark blue solid. Purification by column chromatography on silica gel (eluent: hexane-DCM 6:4) followed by an acetone wash gave the title compound as a dark blue powder (0.8g, 42%). Greater than 99% pure by HPLC.  $^1\text{H}$  NMR (300.13 MHz,  $\text{CDCl}_3$ )  $\delta$ (ppm) 1.36-1.39 (m, 42H) 7.67 (s, 4H) 9.12 (s, 4H);  $^{13}\text{C}$  NMR (125.77 MHz,  $\text{CDCl}_3$ )  $\delta$ (ppm) 11.72, 19.04, 20.56, 105.11, 106.23, 117.68, 124.49, 127.09, 130.42, 131.84, 136.37

4. Synthesis of Anthra[2,3-*b*:6,7-*b'*]dithiophene-5,11-dione Formula F<sub>1</sub> and Anthra[2,3-*b*:7,6-*b'*]dithiophene-5,11-dione Formula F<sub>2</sub>

Formula F<sub>1</sub>Formula F<sub>2</sub>

To a solution of thiophene-2,3-dicarbaldehyde (1.00g, 7.1mmol, 2 molar equivalents) and 1,4-cyclohexanedione (0.40g, 3.6mmol, 1 molar equivalent) in ethanol (100ml) was added a solution of 5% aqueous NaOH (3ml) at room temperature. The reaction mixture was stirred for 30 minutes at room temperature and then warmed to 60°C. After 1 hour at 60°C, the reaction mixture was cooled to room temperature. The resulting precipitate was filtered, washed with water (20 ml), ethanol (40 ml) and diethyl ether (40 ml) to give the title compound a yellow powder (1.02g, 89%). IR (selected bands) 1667 (quinone), 1573, 1318, 1283 cm<sup>-1</sup>.

5. Synthesis of 5,11-bis(triisopropylsilyl)ethynylanthra[2,3-b:6,7-b']dithiophene Formula G<sub>1</sub> and 5,11-bis(triisopropylsilyl)ethynylanthra[2,3-b:7,6-b']dithiophene Formula G<sub>2</sub>

Formula G<sub>1</sub>Formula G<sub>2</sub>

To a solution of triisopropylsilylacetylene (2.1mL, 9.4mmol, 6 molar equivalents) in THF (50ml) cooled to -78°C was added dropwise a 2.5M solution of *n*-butyllithium in hexane (3.4mL, 8.5mmol, 5.5 molar equivalents). The solution was stirred at -78°C for 45 minutes and anthradithiophene-5,11-diones (Formula F<sub>1</sub> and F<sub>2</sub>) (0.5g, 1.6mmol, 1 molar equivalent) were added. The reaction mixture was warmed and stirred overnight at room

temperature. A solution of 10% aqueous HCl saturated with  $\text{SnCl}_2$  (5ml) was added at room temperature and the reaction mixture was stirred at 50°C for 45 minutes. On cooling a solution of 2M aqueous solution of  $\text{Na}_2\text{CO}_3$  (5ml) was added and the resulting solution was stirred with celite for 5 minutes. The solution was filtered through celite and concentrated under vacuum to give a dark red solid. Purification by column chromatography on silica gel (eluent: hexane-DCM 8:2) followed by an acetone wash gave the title compound as a dark red powder (0.45g, 44%). Greater than 99% pure by HPLC (Syn and anti isomers co-elute).  $^1\text{H}$  NMR (500.13 MHz,  $\text{CDCl}_3$ )  $\delta$  (ppm) 1.37-1.39 (s, 42H) 7.42 (d,  $J=5.50$  Hz, 2H) 7.54 (dd,  $J_1=5.50$ ,  $J_2=2.00$  Hz, 2H) 9.15 (s, 2H) 9.19 (s, 2H);  $^{13}\text{C}$  NMR (125.77 MHz,  $\text{CDCl}_3$ )  $\delta$ (ppm) 11.26, 11.65, 18.74, 18.96, 104.13, 104.20, 105.61, 105.89, 106.16, 117.62, 118.92, 120.02, 120.06, 121.31, 121.37, 123.75, 129.76, 129.78, 129.85, 129.88, 129.96, 130.06, 139.46, 139.61, 139.96, 140.06

#### Determination of the Field Effect Mobility

The field effect mobility of the materials was tested using the techniques described by Holland et al, J. Appl. Phys. Vol.75, p.7954 (1994).

In the following examples a test field effect transistor was manufactured by using a PEN substrate upon which were patterned Pt/Pd source and drain electrodes by standard techniques, for example shadow masking. Semiconductor formulations were made using TIPS (formula B above) blended with an inert binder resin (poly(alpha-methylstyrene)). The semiconductor formulation was dissolved one part into 99 parts of toluene, and spin coated onto the substrate at 500 rpm for 18s. To ensure complete drying the sample was placed in an oven for 20 minutes at 100°C. For comparison films of purely TIPS material were coated by spin coating. These were then dried in an oven for 20 minutes at 100°C. The insulator material (Cytop 107M, Asahi glass) was mixed 3 parts to 2 parts of perfluorosolvent (FC75, Acros cat. no. 12380) and then spin-coated onto the semiconductor giving a thickness typically of approximately 1  $\mu\text{m}$ . The sample was placed once more in an oven at 100°C to evaporate solvent from the insulator. A gold gate contact was defined over the device channel area by evaporation through a shadow mask. To determine the capacitance of the insulator layer a number of devices were prepared which consisted of a non-patterned Pt/Pd base layer, an insulator layer prepared in the same way as that on the FET device, and a top electrode of known geometry. The capacitance was measured using a hand-held multimeter, connected to the metal either side of the insulator. Other defining parameters of the transistor are the length of the drain and source electrodes facing each other ( $W=30$  mm) and their distance from each other ( $L=130$   $\mu\text{m}$ ).

The voltages applied to the transistor are relative to the potential of the source electrode. In the case of a p type gate material, when a negative potential is applied to the gate, positive charge carriers (holes) are accumulated in the semiconductor on the other side of the gate dielectric. (For an n channel FET, positive voltages are applied).

This is called the accumulation mode. The capacitance/area of the gate dielectric  $C_i$  determines the amount of the charge thus induced. When a negative potential  $V_{DS}$  is applied to the drain, the accumulated carriers yield a source-drain current  $I_{DS}$  which depends primarily on the density of accumulated carriers and, importantly, their mobility in the source-drain channel. Geometric factors such as the drain and source electrode configuration, size and distance also affect the current. Typically a range of gate and drain voltages are scanned during the study of the device. The source-drain current is described by Equation 1.

$$I_{DS} = \frac{\mu W C_i}{L} \left( (V_G - V_0) V_{DS} - \frac{V_{DS}^2}{2} \right) + I_{\Omega}, \quad \text{Equation 1}$$

where  $V_0$  is an offset voltage and  $I_{\Omega}$  is an ohmic current independent of the gate voltage and is due to the finite conductivity of the material. The other parameters have been described above.

For the electrical measurements the transistor sample was mounted in a sample holder. Microprobe connections were made to the gate, drain and source electrodes using Karl Suss PH100 miniature probe-heads. These were linked to a Hewlett-Packard 4155B parameter analyser. The drain voltage was set to -20 V and the gate voltage was scanned from +20 to -60V and back to +20V in 1 V steps. In accumulation, when  $|V_G| > |V_{DS}|$  the source-drain current varies linearly with  $V_G$ . Thus the field effect mobility can be calculated from the gradient (S) of  $I_{DS}$  vs.  $V_G$  given by Equation 2.

$$S = \frac{\mu W C_i V_{DS}}{L} \quad \text{Equation 2.}$$

All field effect mobilities quoted below were calculated from this regime (unless stated otherwise). Where the field effect mobility varied with gate voltage, the value was taken as the highest level reached in the regime where  $|V_G| > |V_{DS}|$  in accumulation mode. The values quoted in table 3 are an average taken over several devices (fabricated on the same substrate), the sample size is also quoted in table 3. An example of the current-voltage and mobility-voltage characteristics for example 1 is shown in figure 1. The forward and reverse scans illustrate the low hysteresis of the device. The results show the excellent charge mobility obtained when the pentacene compound is combined with the binder resin at up to 50 % wt.

Table 3: results of the formulations tested

Example number	Organic semiconducting material (OSC)	Binder	OSC : binder ratio (wt:wt)	OSC coating method	Mobility [ $\text{cm}^2/\text{Vs}$ ]	Sample size
1	Formula B	p- $\alpha$ MS	50:50	Spin coat	0.433	9
2	Formula B	p- $\alpha$ MS	75:25	Spin coat	0.321	7
3	Formula B	p- $\alpha$ MS	90:10	Spin coat	0.327	6
4	Formula B	p- $\alpha$ MS	95:5	Spin coat	0.244	8
5 (comparative)	Formula B	-	100	Spin coat	0.138	6

p- $\alpha$ MS = Poly(alpha-methylstyrene), Aldrich catalogue number 19,184-1.




Figure 1 : Current voltage characteristics of a transistor fabricated using semiconductor formulation in example 1 (drain source voltage  $-5\text{V}$ , note drain current has been multiplied by  $-1$  to display correctly on log scale).

# Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/GB04/004973

International filing date: 25 November 2004 (25.11.2004)

Document type: Certified copy of priority document

Document details: Country/Office: GB  
Number: 0414347.5  
Filing date: 26 June 2004 (26.06.2004)

Date of receipt at the International Bureau: 02 March 2005 (02.03.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland  
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record.**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☒ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**